



Manufacturer of Industrial,
Protective, Marine Traffic, Automotive
& Decorative Paints



Alkyd Enamel Matt Paint KRS-101



Technical Data

Color: White (other colors are available based on customer order)

Description & Recommended Use

Alkyd Enamel Matt Paint (QUEEN) is made of alkyd resins based and also the most recent formula available in paint industry with compatibility to various climates.

This paint has a suitable drying time, durability and good adhesion and shows a good resistance against climatic factors so it is recommended for interior areas and all metal, wood, plaster, cement, brick surfaces.

Specification

- Washable 100%.
- Suitable drying time.
- Excellent coverage.
- Abrasion resistant.
- Sunlight and UV resistant

Technical Specifications (White) At 25°C

- Theoretical coverage: 10-11 m²/lit
- Recoat Time: 12 hours
- Flash Point: 38°C
- Resin Type: Alkyd

Application Method

Brush, Spray and Roller

Application procedure

clean the surface from any contamination and grease and wait till complete drying. In order to get a flat surface, old paint flakes must be cleaned from the surface. (If needed you can use sandpaper to remove the old paints). Brush must be used for cleaning the surface saltpetre.

Metal surfaces must be cleaned from any rusts and filing.

Repair surface with related construction materials. It's recommended to use oily putty for wooden and metal surfaces and plaster and oily putty for interior surfaces of building.

After repairing surface, you can flatten bulging points with scraper and drawshave and according to flatness or roughness that you consider, you can sandpaper the whole surface.

After general preparation and before applying paint, it's recommended to use alkyd enamel paint (undercoat) for plaster, cement and wooden surfaces and anti corrosion (anti corrosion primer) for metal surfaces as primary layer. In this stage and according to necessity and achieving a flat surface, you may continue puttying and polishing it, with sandpapering.

Dilute Alkyd enamel matt paint (QUEEN) with proper amount of white spirit solvent and apply it by brush, roller or paint gun on the surface.

Dilution ratio of paint with white spirit depends on temperature, surface and painting tools. But in normal weather conditions amount of dilution with paint base on weight percentage is as follows: brush 25%, roller 20% and paint gun 45%



Factory: No727, Aven. Afra, Abas abad industrial state
Boostan Ave, Velenjak St, Tehran, IRAN



Phone: (+98)21-364 247 92-4
(+98)21-364 232 95-7



Manufacturer of Industrial,
Protective, Marine Traffic, Automotive
& Decorative Paints



Solvent

White Spirit

Recommendations

Before using, stir the content well.

Add the necessary amount of white spirit thinner to paint slowly and simultaneously mix it.

During painting, open doors and windows in order to flow of fresh air

How To Clean Tools

After use, wash your hands and painting tools with white spirit. Follow manufacturer's safety recommendations when using white spirit

Safety Points and Storage Conditions

Keep the paint in dry and cool place, far from the direct sunlight.

Keep the can closed after use. It is recommended to use this product before the expire date (Maximum 9 months).

While applying, use a suitable air conditioning and leave the doors and windows open. In case of epiphora, headache or other diseases, breath more fresh air or use fitted respirators (NIOSH approved) or leave the working area. Avoid eye touch, in the case of touch wash it with lots of water. Wash your hands after use. If swallowed, go to medical centers.

Sanding or scraping the old alkyd painted surface can cause poisonous lead dust. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure of lead or other hazardous substances requires the use of proper protective equipment, such as proper fitted respirator (NIOSH approved) and proper containments. Finally, clean up your working area proper fitted respirator (NIOSH approved) and proper tools. Finally, clean up your working area.



Factory: No727, Aven. Afra, Abas abad industrial state
Boostan Ave, Velenjak St, Tehran, IRAN



Phone: (+98)21-364 247 92-4
(+98)21-364 232 95-7

